



# Tennis Court

## PRODUCT DESCRIPTION

Tennis Court is specifically formulated, using an acrylic emulsion polymer, to provide a flexible, long lasting & weather resistant coating.

## PRODUCT FEATURES

Tennis Court is a hard wearing dressing for surfacing old and new concrete courts as well as good tarmac surfaces which have weathered properly and have settled down.

## TECHNICAL INFORMATION

Colour: Green  
 Appearance: Low sheen finish  
 Generic type: Pure acrylic  
 Total solids: 46 – 50 %  
 Recommended DFT: 30 microns per coat  
 S.G.: 1.34  
 Viscosity: 72 - 82ku  
 Spreading rate: 6m<sup>2</sup>/litre (depending on porosity of substrate)  
 Solvent: Water  
 Packaging: 1 litre, 5 litre, 20 litre containers

## SURFACE PREPARATION

All surfaces must be swept, clean and dry. Remove any fungus or algae using Biocidal Wash and suitable scrubbing.  
 Remove grease, dirt, oil etc. with O'Grady's Sugarsoap and rinse thoroughly with fresh water. Remove any loose and flaking paint. Remove any laitance on new concrete by sandblasting or other forms of abrasion.  
 Concrete courts may be painted as soon as it is dry.  
 Tarmac surface must be left for at least 12 months to settle before painting.

## APPLICATION

Stir content well with a flat paddle until completely homogeneous.  
 For new work and bare touch up areas dilute the first coat in the ratio of 1 part paint : 3 parts water.  
 For subsequent coats or when applying to previously painted surfaces, dilute 1 : 1 with water.  
 Apply by roller, brush, squeegee.  
 Clean up: Do not allow to dry on or in equipment, wash immediately with water

## ENVIRONMENT

It is recommended that application be confined to the following:

Surface temperature: Min. 15°C Max. 40°C  
 Ambient temperature: Min. 15°C Max. 40°C  
 Relative humidity: Min.0% Max.75%  
 Or at least 3°C above Dew point

Do not leave container open, as skin quickly forms on the surface of the paint.

## DRYING TIME

Substrate Temp	Touch Dry	Hard Dry
15°C	2 hours, 30 min	18 hours
20°C	1 hour, 15 min	12 hours
25°C	45 minutes	8 hours
30°C	30 minutes	4 hours

## OVERCOATING TIMES

15°C: 24 hours  
 20°C: 16 hours  
 25°C: 12 hours  
 30°C: 10 hours

At no time should Tennis Court be applied outdoors in inclement weather of before 9am & after 2pm in winter, as this can result in white spotting & pigment wash out.

## STORAGE AND HANDLING

Store in a cool dry area, away from heat & severe cold.  
 Shelf life: 1 year in original sealed containers

## LIMITATIONS

Temperatures below 15°C can result in failure & we therefore do not recommend painting in sustained cold conditions. Avoid wet conditions & wet substrates.

## SAFETY PRECAUTIONS

No known problems resulting from contact with skin, however remove as soon as possible with soap and water. Avoid ingestion and contact with eyes. If ingested seek medical attention. Do not induce vomiting. If paint contact is made with eyes, rinse eyes well with water & seek medical attention. Do not smoke when painting. Ensure good ventilation during painting and drying.

KEEPOUTOFREACHOFCHILDREN.

Information Provided is based on Laboratory evaluations and data believed to be reliable.  
 Recommendations are given in good faith but without warranty. It is the user's responsibility to determine the suitability for their own use.  
 It is not to be considered a guarantee of the products properties.  
 For more information contact our Factories:  
 Western Cape: Tel/Fax: (021) 853-8105 Mpumalanga: Tel: (013) 246-2570 Fax: (013) 246-2573